

# MOLYDUVAL

## Pegasus LKA 1 PMV



### Synthetic High Temperature Grease

A light coloured, synthetic high temperature grease for the long-term lubrication with high temperatures. Very good water resistance and good corrosion protection, may be used in humid or damp environment up to +200°C. The good oxidation resistance and the use of thermic stable PAO base fluids withstand short temperature peaks over 200°C, the grease life will then however reduced and it must be relubricated more often.

#### Characteristics

- good anticorrosive properties
- high temperature resistance
- strong tackiness
- good walking resistance
- fully synthetic
- resistant to water
- good sealing properties
- very good low-temperature characteristics

#### Applications

- for bearings in high temperature sectors, ventilators, ovens, motors
- for bearings of oven conveyors, as in annealing and drying furnaces, bakery ovens, rotary kilns
- for small gear boxes
- for anti-friction and sleeve bearings at high temperatures, in ovens, ventilators, engines
- for preparation of bearings and guidelines
- for anti-friction bearings in paper production in dry or wet areas
- for high speed bearings in high speed drives

#### Technical Datas

Color		beige
Base Fluid		PAO
Name		ISO-L-XEDHB1
Name		KHCP1N-50
Consistency Class NLGI		1
Viscosity Base Fluid, 40°C	mm <sup>2</sup> /s	150
Density 15°C	kg/m <sup>3</sup>	910
Temperature Range	°C	-50 -> +140
Temperature Range shortly up to	°C	180
Dropping Point	°C	260
Lubricating Ability 02-SKF-R2F 140°C		pass
Water Resistance Static	Grade	1
Corrosion Protection Emcor, WWO, distilled water	Grade	0-0
Corrosion Protection copper	Grade	1

*The indicated service temperatures are guide values depending on the lubricants composition and on the application. They may vary in case of special influences or ongoing use.*

For further information, please see our website [www.molyduval.com](http://www.molyduval.com) or consult your local representative.

The content of this manual is based on our current knowledge and experience in the development and manufacture of lubricants. Because of the complexity of tribological systems, the effect of our products depends on many parameters, which we cannot assess and which influence we cannot evaluate. For this reason general statements about the function of our products are not possible. The information in this manual, therefore, contains non-binding guidelines, which should give the technical trained reader information on possible applications. The information in this manual does not include property assurances or warranties or guarantees to the properties or suitability of this product in a specific application. Prior to its use it is absolutely necessary to test this product in the application to ensure that the product and its use is safe, economical and fully suitable. It should proceed with due diligence. We reserve the right to change the information in this manual at any time and without notice. All previous versions of this manual are no longer valid. Updating : 03.06.2024