



MOLYDUVAL

Aero 92



Synthetic Low Temperature Grease

A modern synthetic low temperature grease for lubrication of rolling and sleeve bearings at low temperatures up to -60°C . It is frost-resistant and contains anti-corrosion additives which provide additional rust protection in case of water or damp may penetrate the lubrication point. It is easy to apply and pump at low temperatures. It is free from particles which can cause noise in the bearings, thus the bearings run more easy and quietly, making it suitable as an instrument grease.

Characteristics

- good anticorrosive properties
- water refusing
- good pressure absorption capacity
- strong tackiness
- extreme frost resistant
- biodegradable
- good walking resistance
- low danger of forming residues or carbon
- relative good compatible with many usually used sealants
- low starting torque
- compatible with many seals and plastics

Applications

- for fittings, for example cocks and plugs
- for anti-friction and sleeve bearings at low or changing temperatures
- for instruments in precision engineering
- for hinges, joints, rails, guidelines
- for anti-friction or sleeve bearings in cooling equipment
- for small gear units in medicinal or pharmaceutical equipment
- for lubrication of small gears at high speed
- for joints in instruments
- for gears of radar or telegraphic equipment
- for tachometer axles
- for door and similar locking systems
- for small roller bearings with high turns

Technical Datas

Color		beige
Base Fluid		PAO
Name		ISO-L-XEDIB2
Name		KPHC2N-60
Consistency Class NLGI		2
Viscosity Base Fluid, 40°C	mm^2/s	27
Density 15°C	kg/m^3	880
Temperature Range	$^{\circ}\text{C}$	$-60 \rightarrow +140$
Temperature Range shortly up to	$^{\circ}\text{C}$	200
Utility Time	h	140
nd value n-d		1.000.000
Dropping Point	$^{\circ}\text{C}$	260
Water Resistance Static	Grade	1-90
Corrosion Protection Emcor, WWO, distilled water	Grade	0

For further information, please see our website www.solano-industries.com/en/

The content of this manual is based on our current knowledge and experience in the development and manufacture of lubricants. Because of the complexity of tribological systems, the effect of our products depends on many parameters, which we cannot assess and which influence we cannot evaluate. For this reason general statements about the function of our products are not possible. The information in this manual, therefore, contains non-binding guidelines, which should give the technical trained reader information on possible applications. The information in this manual does not include property assurances or warranties or guarantees to the properties or suitability of this product in a specific application. Prior to its use it is absolutely necessary to test this product in the application to ensure that the product and its use is safe, economical and fully suitable. It should proceed with due diligence. We reserve the right to change the information in this manual at any time and without notice. All previous versions of this manual are no longer valid. Updating : 06.11.2024

MOLYDUVAL

Aero 92

Technical Datas

Corrosion Protection copper	Grade	1
Pack Size tube 100 g		+
Pack Size cartridge 400 g		+
Pack Size round box 1 kg		+
Pack Size pail 5 kg		+
Pack Size pail 18 kg		+

The indicated service temperatures are guide values depending on the lubricants composition and on the application. They may vary in case of special influences or ongoing use.

The indicated speed factors are guide values which depend on the type and diameter of the bearing and the local operating conditions, which is why they have to be confirmed in tests carried out by the user in each individual case.



For further information, please see our website www.solano-industries.com/en/

The content of this manual is based on our current knowledge and experience in the development and manufacture of lubricants. Because of the complexity of tribological systems, the effect of our products depends on many parameters, which we cannot assess and which influence we cannot evaluate. For this reason general statements about the function of our products are not possible. The information in this manual, therefore, contains non-binding guidelines, which should give the technical trained reader information on possible applications. The information in this manual does not include property assurances or warranties or guarantees to the properties or suitability of this product in a specific application. Prior to its use it is absolutely necessary to test this product in the application to ensure that the product and its use is safe, economical and fully suitable. It should proceed with due diligence. We reserve the right to change the information in this manual at any time and without notice. All previous versions of this manual are no longer valid. Updating : 06.11.2024