

LOXEAL INSTANT ADHESIVE 74

Description

Rubber toughened low viscosity Ethyl-Cyanoacrylate adhesive with increased flexibility and impact resistance. Suitable for bonding rubbers and metals. Curing time is designed to allow right positioning of the pieces before assembly. Good temperature resistance up to +120°C.

Physical properties

Composition:	ethyl cyanoacrylate modified
Colour:	black
Viscosity (+25°C - mPa s):	100 - 200
Specific weight (g/ml):	1,06
Gap to fill:	10 - 150 microns
Flash point:	see MSDS
Shelf life:	6 months in original unopened packaging
Temperature range	-50°C/+100°C

Curing properties

Curing rate depends on the substrate used, on the gap, on the temperature and on the environmental humidity.

<u>Substrate</u>	<u>Fixturing Time (seconds)</u>
------------------	---------------------------------

Plastics

* PVC:	20 - 50
* Phenolic Resin:	10 - 40
* ABS:	15 - 40

Metals

* Steel:	20 - 50
* Aluminium:	10 - 60
* Zinc:	10 - 60

Various substrates

* Neoprene/NBR:	< 30
-----------------	------


In case of too long setting time we recommend to use Loxeal Activator 9. IN case of usage with PE, PP, Silicone rubbers or PTFE Loxeal Primer 7 is always recommended.

Proprieties of cured material (typical)

Tensile strength ISO 6922 (N/mm ²):	12 - 25
Shear strength ISO 4587 (N/mm ²):	15 - 25
Softening range:	+160°C/+170°C
Refraction index n ^{20D} :	similar to glass
Electrical resistivity DIN 53482 (Ω mm):	>10 ¹⁵
Dielectric strength ASTM D 149 (kV/mm):	25
Dielectric constant DIN 53483 (1MHz):	5,2

Environmental resistance

The graph below shows the mechanical strength of the product (%) vs. temperature.
Specimen steel - ISO 4587



Chemical resistance

Aged at indicated temperature under conditions below after 24 hours from polymerisation.

Substance	°C	Resistance after 100 h	Resistance after 500 h	Resistance after 1000 h
-----------	----	------------------------	------------------------	-------------------------

Motor oil	40	good	good	good
Alcohol	25	excellent	excellent	discrete
Gasoline	25	excellent	discrete	discrete
Relative humidity 90%	40	discrete	discrete	low
Refrigerating gases	25	good	good	good

* For information on resistance with other chemicals, contact Loxeal Technical Service

Directions for use

1. Clean and degrease all surfaces with Loxeal Cleaner 10 and allow drying before applying the adhesive.
2. For bonding low surface energy plastics such as PE, PP, PTFE, apply Loxeal Primer 7 on bonding surfaces and allow drying.
3. To reduce curing time of some hard to bond rubbers and plastics, using Activator 9 is recommended. After its application on one surface, let it dry. Any surplus adhesive outside the joint can be instantaneously fixed with Activator 9 after assembling.
4. Use the proper bottle to apply the adhesive, avoiding the usage of improper tools. Bring the components together quickly and correctly aligned (fast curing does not allow any repositioning).
5. Apply sufficient pressure for a few seconds to fix the components and clamp them until they are completely fixed.
6. Wait 24-72 hours until full cure before any mechanical stress.

Warnings

This adhesive is not approved for usage neither with pure nor with gaseous oxygen. Storage

We recommend to store product in a cool and dry place at temperature non-exceeding +20°C. For better and enhanced shelf life, keep product in a refrigerator at +2°C/+7°C. To avoid contaminations do not refill containers with used product. For more information on applications, storage and handling contact Loxeal Technical Service

Safety and handling

Consult the Safety Data Sheet before use.

Note

The data contained herein, obtained in Loxeal laboratories, are given for information only; if specifics are required, please contact Loxeal Technical Department. Loxeal ensures abiding quality of supplied products according to its own specifics. Loxeal cannot assume responsibility for the results obtained by others which methods are not under Loxeal control. It is user's responsibility to determine suitability for user's purpose of any product mentioned herein. Loxeal disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loxeal products. Loxeal specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.